
acoufelt



Beam

Ceiling Baffle

WoodGrain Collection

Beam Ceiling Baffles offer a striking and versatile way to absorb unwanted sound. Available in a variety of sizes and made with exacting precision, the Beam baffles can easily become the focal point of a space. The long, lean design of Beam baffles maximizes sound absorption with a minimalist aesthetic.

Specifications

Surface	Ceiling
Material	FilaSorb™ polyester felt
Weight	2400gsm
Standard Sizes	Height: 200mm up to 400mm H (50mm increments) Thickness: 50, 76, 102mm T Length: 3000 up to 5500mm L (600mm increments)



Beam Ceiling Baffles in French Bobbin

Technical

NRC Rating	1.65*
Fire Test	AS ISO 9705:2003 (according to AS 5637.1:2015 requirements) Group 1 0.93
Water Sorption	ASTM C1104-2019 (A Modified) Water sorbed by weight: 0.20% (based on a 12mm thick panel)
Colorfastness	ISO 105-B02, 6-7

** Test results available upon request.*

Details

Lead Time	Refer to Product Lead Time Matrix
Origin	Australia
Warranty	Product: 20 years* Colorfastness: 20 years*

** Conditions apply*

Environmental

Recycled Content	Minimum 60%
Energy	Generated using 40% solar energy
Indoor Air Quality	VOC less than/equal to 0.5mg/m3
Recyclable	100%*
Certifications	Declare Certification - LBC Red List Free (third-party verified) SCS Global Indoor Advantage Gold

** PET is recyclable through participating partners.*

© 2026 Acoufelt. All rights reserved.

Colorways

WOODGRAIN



Picket Fence
WQ01



Loft
WQ06



White Elm
WQ07



Lyed Larch
WQ30



White Oak
WQ13



Baltic Birch
WQ12




Knotty Spruce
WQ29



French Bobbin
WQ08



Boat Shed
WQ02



Nordic Plank
WQ15




Boardwalk
WQ10



Mocha Legno
WQ25



Mountain Lodge
WQ24



Wine Barrel
WQ03



Log Cabin
WQ04



Natural Oak
WQ16



Woodland Fog
WQ22




Driftwood
WQ21



Weathered Slate
WQ14




Petrified Ash
WQ23




Antique Chest
WQ11



European Larch
WQ17



Fumed Oak
WQ19



Teak
WQ18



Charred Larch
WQ09



Shadow Oak
WQ28



Barn Door
WQ05



Black Walnut
WQ20



Scorched Timber
WQ26



Espresso Oak
WQ27


© 2026 Acoufelt. All rights reserved.

Sizes


Standard Sizes

Height: 200mm up to 400mm H (50mm increments)
Thickness: 50, 76, 102mm T
Length: 3000mm up to 5500mm L (600mm increments)


Elevation





Plan





Visible Seam Spacing












© 2026 Acoufelt. All rights reserved.


Hardware Spacing

3048mm L	1830mm on center spacing
3658mm L	2440mm on center spacing
4267mm L	2440mm on center spacing
4878mm L	2440mm on center spacing
5486mm L	3050mm on center spacing


3048mm L




4267mm L




3658mm L



4878mm L




5486mm L




© 2026 Acoufelt. All rights reserved.

Mounting Methods


Cable




Cable to deck




Swivel cable to deck




Cable to T-grid



Threaded Rod




Magnet to T-grid




Mounting Methods cont'd.

Twist lock to T-grid



Acoustic Performance

Test Method	ASTM E795-16
Install Method	J-600
Rating Method	ASTM C423-17
Mounting Method	Sample tested 5 baffles 2800mm L x 305mm H x 76mm T, hanging 600mm from floor and 152mm from each other
Test Results	NRC 1.65 SAA 1.68



Frequency f (Hz)	125	250	500	1000	2000	4000	NRC
76mm Truss Baffle	0.26	0.86	1.25	2.02	2.49	2.49	1.65

What is a Noise Reduction Coefficient (NRC)?

You'll find the NRC rating in the specifications of all of our products. This acronym stands for Noise Reduction Coefficient, and is expressed as a single number, a rating that describes the degree to which acoustic products can absorb sound.

You can use NRC values to understand the overall performance of our acoustic wall and ceiling products. The higher the NRC, the better the product is at soaking up the sound.

Performance Indices: Noise Reduction Coefficient (NRC) results represent the absorption coefficients measured at the one third octave bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customization of installation of the product could alter the results. Sound Absorption Average (SAA) indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz.

© 2026 Acoufelt. All rights reserved.