

Escape QuietBackTM Carpet Tiles

Specifications

Application Floor

Backing Felt polyester

Pile content Solution dyed nylon

Multi-level textured loop pile Style

Recycled content Backing made from

>90% recycled PET

Dimensions 500 x 500mm **Thickness** 8mm +/- 10%

Tiles per box 20

Classification Commercial Extra Heavy Duty*

*conditions apply

Guarantees

Wear warranty 20 years* Castor chair proof 20 years* Lifetime* **Anti-static** Colorfastness warranty 20 years*

*conditions apply

Shipping



QuickShip

QuickShip products can be despatched within 24 hours.

Technical Data

Fire test method AS/ISO 9239.1-2003 Mean result 7.4kW/m² Critical heat flux Mean result 175%.min Smoke deviation rate **Dimensional stability** -0.05% Electrostatic propensity <0.3000 kv $0.2m^2K/W$ Thermal resistance Total VOC test method SCS-EC10.3-2014 v4.0 meeting standard CDPH/EHLB Standard Method v.1.2-2017 **Total VOC result** ≤ 0.5mg/m³ or less Colorfastness test method ISO 105-B02 6-7 Rating HN 0028-2004 Determination of Mildew and Odour Mildew Growth and Odour on Trim Material. **Rating** = satisfactory **Antimicrobial** AATTCC Method 174:2016 Part II effectiveness Rating = <100

Sustainability



Backing made from 90% min. recycled PET





Environmental Product Declaration in accordance with ISO 14025 and EN 15804. ACCS, Environmental Certification Scheme Level 4 Compliant











Acoustic Performance


Test ASTM C423-2022: Standard Test Method for method Sound Absorption and Sound Absorption

Coefficients by the Reverberation Room Method

Ratina AS ISO 11654 -2002: Acoustics - Rating of sound method

absorption - Material and systems

Test results NRC 0.40 | SAA 0.38



Frequency (Hz)	125	250	500	1000	2000	4000	NRC
α_{s}	0.01	0.08	0.40	0.41	0.46	0.55	0.40

Performance Indices: Noise Reduction Coefficient (NRC) results represent the absorption coefficients measured at the one third octaves bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according alter the results. **Sound Absorption Average (SAA)** indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz

Configurations




Quarter




Non-

Directional







Directional

Brick

Ashlar



Colorways

