

# Formation Panels



## **Specifications**

Application Wall Composition 100% polyester FilaSorb™ Material Recycled content 60% min. rPET Thickness 12mm +/- 10% Weight 2400gsm Width – 1220mm Dimensions Depth - 152mm (max), 35mm (min) Height - 2440 & 2800mm

# Sustainability



Made from 60% min. recycled content




Declare Red List Free (3<sup>rd</sup> Party Verified)

Generated using 40% solar energy





Total VOC's less than 0.5 mg/m<sup>3</sup> (3<sup>rd</sup> Party Verified)



### Guarantees

**Technical Data** 

Lead Time	6-8
Origin	Unit
Warranty against defects	20 y
Colourfastness warranty	20 y

weeks ted Kingdom vears\* vears\*

\*conditions apply

# Acoustic Performance

#### Test method

Installation method

Mounting method A


### Rating method

sytems

#### Test results 12mm

as)

no air gap - 0.45 NRC | 0.25 (H) aw no air gap, Class E 12mm air gap - 0.54 NRC | 0.35 (MH) aw 12mm air gap, Class D 20mm air gap - 0.64 NRC | 0.40 (MH) aw 20mm air gap, Class D \*results are for materials only



Frequency f (Hz)

Frequency (Hz)	125	250	500	1000	2000	4000	NRC	Class Rating
12mm - a₅no air gap	0.06	0.02	0.23	0.61	0.89	0.95	0.45	Class E
12mm - a₅ 12mm air gap	0.03	0.14	0.33	0.74	1.00	1.00	0.54	Class D
12mm - a₅ 20mm air gap	0.05	0.16	0.48	0.85	1.00	1.00	0.64	Class D

Performance Indices: Noise Reduction Coefficient (NRC) results represent the absorption coefficients measured at the one third octaves bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customisation of installation of the product could alter the results.

BU SADES BUREAU VERFAS Centificative	INDOOR ADVANTAGE GOLD	Red List Free Verified		had
E0 9901 BUREAU VERTAS Gentrades		Declare.	MADE IN BRITAIN	VERSION 2.3


12mm ASTM C423-09a: Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method

AS ISO 11654 -2002: Acoustics - rating of sound absorption - material and

\*Graph not to scale.



# Formation Designs



Concave

Convex

Monument

Perch




### Formation Sizes


#### Sizes


Width	1220mm
Depth	152mm (Max), 35mm (Min)
Height	2440 & 2800mm
Thickness	12mm

#### Design Profile



#### Elevation







# FilaSorb<sup>TM</sup> Colourways



#### Can't find a colour?

We are constantly updating our palette, which includes adding and discontinuing certain colour lines. If you can't find the colour you are looking for, please contact us with your colour request, as we may still have stock available.






Oregano OR18



Azur AZ05





Platinum PL04



Sencha SE58



Marine MA15



Milkyway MI74



# Mounting Methods

#### Construction Adhesive

