

Regular Ceiling Tiles

Specifications

Application Ceiling

Material FilaSorb™ polyester felt

Recycled content 60% min. rPET
Thickness 12 & 22mm +/- 10%

Weight 2400gsm

Dimensions 595 x 595mm

595 x 1195mm

Custom size available upon request

Qty per carton $595 \times 595 \text{mm} = 8$

595 x 1195mm = 4

Technical Data

12mm

Fire test method AS ISO 9705:2033

(according to AS 5637.7:2015 requirements)

Group number Group 1 **SMOGRA**_{RC} (in m2/s2 x 1000) 0.93

22mm

Fire test method AS ISO 9705:2033

(according to AS 5637.7:2015 requirements)

Group number Group 1 **SMOGRA**RC (in m2/s2 x 1000) 0.61

12 & 22mm Total VOC test method SCS-EC10.3-2014 v4.0 meeting standard CDPH/EHLB Standard Method v.1.2-2017 Total VOC result $\leq 0.5 \text{mg/m}^3$ Colorfastness test method ISO 105-B02 6-7 Rating Water vapour sorption method ASTM C1104-2019 (Procedure A Modified) Water sorbed by weight 0.20% (results based on a

Details

Lead time2-3 weeksOriginAustraliaWarranty against defects20 years*Colorfastness warranty20 years*'conditions apply

Sustainability



Made from 60% min. recycled content



Material 'Take Back' program allows our product to be recycled



Acoustic Felt material is made with 30-40% solar energy*





12mm thick panel)



12mm Acoustic Performance

Test AS ISO 354-2006: Acoustic - Measurement of method sound absorption in a reverberation room

Installation Method A Method E

method no air gap, 12mm air E-200 12mm air gap, gap, 20mm air gap E-400 400mm air gap

Rating ISO 11654-1997: Acoustic – sound absorbers for use in buildings – rating of sound absorption

Test results Method A Method E

NRC 0.45 no air gap


NRC 0.85 200mm air gap

NRC 0.54 12mm air gap

NRC 0.80 400mm air gap

NRC 0.64 20mm air gap

SAA 0.43 no air gap SAA 0.86 200mm air gap SAA 0.54 12mm air gap SAA 0.83 400mm air gap



Frequency (Hz)	125	250	500	1000	2000	4000	NRC
as no air gap	0.06	0.03	0.23	0.61	0.89	0.55	0.45
a _s 12mm air gap	0.03	0.14	0.33	0.74	1.00	1.00	0.54
a _s 20mm air gap	0.05	0.16	0.48	0.85	1.00	1.00	0.64
a₅ 200mm air gap	0.40	0.75	0.90	0.85	0.95	1.00	0.85
a _s 400mm air gap	0.55	0.75	0.70	0.90	0.95	1.00	0.80

22mm Acoustic Performance

Test AS ISO 354-2006: Acoustic - Measurement of sound absorption in a reverberation room

Installation A, tested with no air gap, method 20mm air gap, 50mm air gap

Rating ISO 11654-2002


method Acoustic – sound absorbers for use in buildings –

rating of sound absorption

Test results NRC 0.65 no air gap

NRC 0.70 20mm air gap NRC 0.70 50mm air gap

SAA 0.63 no air gap SAA 0.69 20mm air gap SAA 0.73 50mm air gap



Frequency (Hz)	125	250	500	1000	2000	4000	NRC
as no air gap	0.05	0.20	0.55	0.80	0.95	1.00	0.65
a₅ 20mm air gap	0.05	0.25	0.60	0.95	0.95	0.95	0.70
as 50mm air gap	0.10	0.35	0.70	0.95	0.95	1.00	0.70

Performance Indices: **Noise Reduction Coefficient (NRC)** results represent the absorption coefficients measured at the one third octaves bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customisation of installation of the product could alter the results. **Sound Absorption Average (SAA)** indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz.



FilaSorb™ 12mm Colorways




We are constantly updating our palette, which includes adding and discontinuing certain color lines. If you can't find the color you are looking for, please contact us with your color request, as we may still have stock available.

22mm Colorways



Mounting Methods

Drop Tile Method



Before installing your tiles, ensure the grid has been installed in accordance with the local building code.

