

Regular Ceiling Panels

Specifications

Application Ceiling

MaterialFilaSorb™ polyester felt

Recycled content 60% min. rPET

Thickness 12, 22 & 24mm +/- 10%

Weight 12mm - 2400gsm

24mm – 4800gsm

Dimensions 1220 x 2800mm

1200 x 2800mm

Custom size available upon request

Technical Data

12mm Fire test method AS ISO 9705:2033 (according to AS 5637.7:2015 requirements) Group number Group 1 0.93 SMOGRARC (in m2/s2 x 1000) 22mm AS ISO 9705:2033 Fire test method (according to AS 5637.7:2015 requirements) Group number Group 1 SMOGRARC (in m2/s2 x 1000) 0.61 24mm

12, 22 & 24mm					
Total VOC test method	SCS-EC10.3-2014 v4.0 meeting standard CDPH/EH Standard Method v.1.2-201				
Total VOC result	≤ 0.5mg/m³				
Colorfastness test method	ISO 105-B02				
Rating	6-7				
Water vapour sorption method	ASTM C1104-2019 (Procedure A Modified)				
Water sorbed by weight	0.20% (results based on a 12mm thick panel)				

Details

Lead time1-2 daysOriginAustraliaWarranty against defects20 years*Colorfastness warranty20 years**conditions apply

Sustainability



Fire test

Made from 60% min. recycled content



Pending

Material 'Take Back' program allows our product to be recycled



Acoustic Felt material is made with 30-40% solar energy*







12mm Acoustic Performance

AS ISO 354-2006: Acoustic - Measurement of Test method sound absorption in a reverberation room

Installation Method A Method E

method no air gap, 12mm air E-200 12mm air gap, gap, 20mm air gap E-400 400mm air gap


ISO 11654-1997: Acoustic – sound absorbers for Rating method use in buildings – rating of sound absorption

Test results Method A Method E

NRC 0.45 no air gap NRC 0.85 200mm air gap NRC 0.54 12mm air gap NRC 0.80 400mm air gap

NRC 0.64 20mm air gap

SAA 0.43 no air gap SAA 0.86 200mm air gap SAA 0.54 12mm air gap SAA 0.83 400mm air gap



	Frequency (Hz)	125	250	500	1000	2000	4000	NRC
	as no air gap	0.06	0.03	0.23	0.61	0.89	0.55	0.45
	a _s 12mm air gap	0.03	0.14	0.33	0.74	1.00	1.00	0.54
	a _s 20mm air gap	0.05	0.16	0.48	0.85	1.00	1.00	0.64
	a _s 200mm air gap	0.40	0.75	0.90	0.85	0.95	1.00	0.85
	a _s 400mm air gap	0.55	0.75	0.70	0.90	0.95	1.00	0.80

22mm Acoustic Performance

Test AS ISO 354-2006: Acoustic - Measurement of method sound absorption in a reverberation room

Installation A, tested with no air gap, method 20mm air gap, 50mm air gap

Rating ISO 11654-2002


method Acoustic - sound absorbers for use in buildings -

rating of sound absorption

Test results NRC 0.65 no air gap

NRC 0.70 20mm air gap NRC 0.70 50mm air gap

SAA 0.63 no air gap SAA 0.69 20mm air gap SAA 0.73 50mm air gap



	Frequency (Hz)	125	250	500	1000	2000	4000	NRC
	as no air gap	0.05	0.20	0.55	0.80	0.95	1.00	0.65
	a₅ 20mm air gap	0.05	0.25	0.60	0.95	0.95	0.95	0.70
	as 50mm air gap	0.10	0.35	0.70	0.95	0.95	1.00	0.70

24mm **Acoustic Performance**

ASTM E795-16: Standard Practices for Mounting Test method Test Specimens During Sound Absorption Tests

Installation A, tested with no air gap


Rating ISO 11654-1997

method Acoustic – sound absorbers for use

in buildings – rating of sound absorption

Test results NRC 0.60 no air gap

SAA 0.55 no air gap



	Frequency (Hz)	125	250	500	1000	2000	4000	NRC
	α_s	0.02	0.57	0.41	0.58	0.87	0.85	0.60

500

2000

*Graph not to scale.

1000

4000

Performance Indices: Noise Reduction Coefficient (NRC) results represent the absorption coefficients measured at the one third octaves bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customisation of installation of the product could alter the results. Sound Absorption Average (SAA) indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz.



FilaSorb™ 12 & 24mm Colorways



Can't find a color?


We are constantly updating our palette, which includes adding and discontinuing certain color lines. If you can't find the color you are looking for, please contact us with your color request, as we may still have stock available.


22mm Colorways



Mounting Methods


Adhesive Method






Panel installation area
Spray adhesive


Pot Magnet Method



Side view




Pot Magnet



Channel Mount Method

Back of panel



Side view Ceiling MDF spacer with metal plate Channel (G1) Panel

Pot Magnet



