

QuietFormTM Panels

Specifications

Application Wall

Material FilaSorb™ polyester felt

Recycled content 60% min. rPET

Weight 2400gsm

Thickness 12mm +/- 10%

Dimensions 1200 x 2800mm

Technical Data

Fire test method AS ISO 9705:2033 (according to AS 5637.7:2015 requirements) Group number Group 1 SMOGRARC (in m2/s2 x 1000) 0.93 Total VOC test method SCS-EC10.3-2014 v4.0 meeting standard CDPH/EHLB Standard Method v.1.2-2017 **Total VOC result** $\leq 0.5 \text{mg/m}^3$ Colorfastness test method ISO 105-B02 6-7 Ratina Water vapour sorption method ASTM C1104-2019 (Procedure A Modified) Water sorbed by weight 0.20% (results based on a 12mm thick panel)

Sustainability



Made from 60% min. recycled content



Material 'Take Back' program allows our product to be recycled



Acoustic Felt material is made with 30-40% solar energy*







Details

Lead time6-8 weeksOriginAustraliaWarranty against defects20 years*Colorfastness warranty20 years**conditions apply

Acoustic Performance

Test method AS ISO 354-2006: Acoustic - Measurement of sound absorption in a reverberation room

Installation method

A, tested with no air gap, 20mm air gap, 50mm air gap

Rating method


ng ISO 11654-1997

Acoustic – sound absorbers for use in buildings – rating of sound absorption

Test results

NRC 0.45 no air gap NRC 0.60 20mm air gap NRC 0.75 50mm air gap

SAA 0.43 no air gap SAA 0.61 20mm air gap SAA 0.72 50mm air gap




	Frequency (Hz)	125	250	500	1000	2000	4000	NRC
	as no air gap	0.00	0.05	0.20	0.55	0.85	1.00	0.45
	as 20mm air gap	0.05	0.15	0.45	0.85	0.95	0.95	0.60
	as 50mm air gap	0.10	0.35	0.70	0.90	0.90	0.95	0.75

Performance Indices: **Noise Reduction Coefficient (NRC)** results represent the absorption coefficients measured at the one third octaves bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customisation of installation of the product could alter the results. **Sound Absorption Average (SAA)** indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz



QuietForm[™] Designs



FilaSorbTM Colorways




Can't find a color?

We are constantly updating our palette, which includes adding and discontinuing certain color lines. If you can't find the color you are looking for, please contact us with your color request, as we may still have stock available.



WoodBeQuiet™ Prints



Mounting Methods

Construction Adhesive

