

Shapes

Specifications

Application Wall

Material FilaSorb™ polyester felt

Recycled content 60% min Weight 2400gsm **Thickness** 12mm +/- 10%

Dimensions Rectangle – 850 x 400mm

> Right Triangle - 300 x 400mm Hexagon - 315 x 400mm Diamond - 350 x 600mm Scale - 400 x 317mm

Ogee - 315 x 400mm

Qty per carton Rectangle - 10

Right Triangle - 54 Hexagon - 24 Diamond - 21 Scale - 32 Ogee - 36

Technical Data

Fire test method	AS ISO 9705:2033 (according to AS 5637.7:2015 requirements)				
Group number	Group 1				
SMOGRARC (in m2/s2 x 1000)	0.93				
Total VOC test method	SCS-EC10.3-2014 v4.0 meeting standard CDPH/EHLB Standard Method v.1.2-2017				
Total VOC result	≤ 0.5mg/m³				
Colorfastness test method	ISO 105-B02				
Rating	6-7				
Water vapour sorption method	ASTM C1104-2019 (Procedure A Modified)				
Water sorbed by weight	0.20% (results based on a 12mm thick panel)				

Sustainability



Made from 60% min. recycled content

Acoustic Felt material

is made with 30-40%

solar energy* *made in Thailand



Material 'Take Back' program allows our product to be recycled



Details

Lead time 2-3 weeks Origin Australia Warranty against defects 20 years* Colorfastness warranty 20 years* *conditions apply

Acoustic Performance

Test AS ISO 354-2006: Acoustic - Measurement of method sound absorption in a reverberation room


Installation A, tested with no air gap method

ISO 11654-1997 Rating method Acoustic – sound absorbers for use

in buildings – rating of sound absorption

Test results NRC 0.45 no air gap

SAA 0.43 no air gap



Frequency (Hz)	125	250	500	1000	2000	4000	NRC
as no air gap	0.06	0.02	0.23	0.61	0.89	0.95	0.45

Performance Indices: Noise Reduction Coefficient (NRC) results represent the absorption coefficients measured at the one third octaves bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customisation of installation of the product could alter the results. Sound Absorption Average (SAA) indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz












Designs




Rectangle 850 x 400mm




350 x 600mm




Right Triangle 300 x 400mm





Hexagon 315 x 363mm



0gee 315 x 400mm

FilaSorbTM Colorways




Can't find a color?

We are constantly updating our palette, which includes adding and discontinuing certain color lines. If you can't find the color you are looking for, please contact us with your color request, as we may still have stock available.



Mounting Methods

Peel and Stick Backing



Construction Adhesive

